

PRODUCT DESCRIPTION

P080101XX / ASA INJ REGRIND

TECHNICAL CHARECTERISTICS

CHARACTERISTIC	VALUE	UNIT	TEST METHOD
Shape	Regrind		Visual
Colour	Unicolour and Multicolour		Visual
Melt mass flow rate (220 °C/10,0 kg)	19,9 – 25,1	g/10 min	EN ISO 1133
Density	1116 – 1128	kg/m ³	EN ISO 1183-1, Method A
Particle size	3,5 – 5,2	mm	EN 15348:2024 (Annex A)
Fine particles	0,2 – 2,1	%	EN 15348:2024 (Annex A)
Non-plastic components' content	<2 (total mass, moisture-free)	%	Internal

► DETERMINATION OF SPECIFICATIONS

Tests carried out, whenever possible, in an accredited laboratory in accordance with the reference standards.

Date: 09/01/2026

The information provided here is prepared in accordance with our knowledge and acquired experience. As there are several factors that may affect the processing and application of our material, this data does not release the processor from the responsibility of carrying out tests that it deems appropriate for the application in question. The data provided does not imply a legal obligation regarding the guarantee of certain properties or suitability for a specific application. This information does not exempt the customer from his obligation to control the product upon entering his premises. It is our customers' responsibility to ensure that they do not conflict with any existing property rights and current legislation.